10 September 2003

US372-1737003
HABS/AKN

C_{7+} Paraffin Isomerisation Process and

Catalyst Therefore

UDL-279

BACKGROUND OF THE INVENTION

The present invention relates to a catalytic process for the production of high-octane gasoline from a hydrocarbon feed stream comprising C_{4+} hydrocarbon cuts in presence of a catalyst composition comprising mixed aluminium and zirconium oxides modified with tungsten oxyanion and hydrogenation/dehydrogenation component of a Group VIII metal.

Multi-branched paraffins are ideal gasoline-blending components possessing high octane numbers. For environmental reasons, there is also a need to find substitutes for aromatic components in gasoline. Therefore, there is an incentive to develop a process for increasing the octane number of the C_4-C_{12} cuts. While C_5/C_6 paraffin isomerisation is a common refinery process, commercialisation of processes including higher fractions (C_{7+} hydrocarbons) meets significant difficulties given by the usually high degree of cracking to gas.

An article by K. Arata and M. Hino in Proceedings 9th International Congress on Catalysis (1988) describes a catalyst based on a Group IVB metal oxide such as zirconia in particular, modified by the oxyanion of the Group VIB, particularly tungstate and its use in paraffin isomerisation.

US Patent No. 5,510,309 provided a method for preparing an acidic solid comprising a Group IVB metal oxide modified with an oxyanion of a Group VIB metal. An example of this acidic solid is zirconia modified with tungstate. This modified solid oxide may be used as a catalyst for example to isomerise C_4 to C_8 paraffins. The modified solid oxide

is prepared by co-precipitating the Group IVB metal oxide along with the oxyanion of the Group VIB metal. Aluminium is mentioned merely as a conventional matrix material such as alumina, silica-alumina and silica with preference given to silica.

Use of tungstated zirconia promoted with noble metal in paraffin isomerisation was described in open literature - S.L. Soled, S. Miseo, J.E.Baumgartner, W.E. Gates, D.G. Barton and E. Iglesia, in: Proc. 13[th] Int. Conf. Catal. (The Taniguchi Foundation, Kobe, Japan, 1994) page 17; E. glesia, D.G. Barton, S.L. Soled, S. Miseo, J.E. Baumgart-ner, W.E. Gates, G.A. Fuentes and G.D. Meitzner, Stud. Surf. Sci. Catal. 101 (1996) 533; G. Larsen, E. Lotero, S. Raghavan, R.D. Parra and C.A. Querini, Appl. Catal. A 139 (1996) 201.

The tungstated zirconia system was frequently described as catalyst for C_{5+} isomerisation. The following patents are variations of the above-mentioned prior art. The catalyst typically contained tungsten oxide in a concentration below 20 wt% and hydrogenation component is platinum. Selectivity of these materials is not sufficient to reach liquid yields above 90% for C_{7+} isomerisation when approaching composi-tion given by thermodynamics. US Patent No. 5,422,327 de-scribes a catalyst composition of a Group VIII metal incor-porated into a support consisting of zirconia, said support being further impregnated with a mixture of silica and tungsten oxide and its use in paraffin isomerisation. US Patent No. 5,648,589 claims a catalytic isomerisation proc-ess comprising contacting a C_{5+} feed under isomerisation conditions with a catalyst composition consisting of a

Group VIII metal and a zirconia support impregnated with tungsten oxide and silica. US Patent No. 5,780,382 provides a method for preparing an acidic solid comprising a Group IVB metal oxide modified with an oxyanion of a Group VIB metal. US Patent No. 5,837,641 describes an isomerisation reaction over tungstated zirconia and the promotional effect of water on this catalyst. US Patent No. 6,080,904 describes a C_4-C_8 isomerisation process utilising an isomerisation catalyst with a hydrogenation/dehydrogenation component (preferentially Pt) and with solid acid component comprising a Group IVB metal oxide modified with an oxyanion of a Group VIB metal.

BRIEF DESCRIPTION OF THE DRAWING

Fig. 1 shows a spectrogram from x-ray analysis of a catalyst according to one embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

The general object of the invention is to provide a process for improving the octane number of a C_{4+} hydrocarbon mixture through isomerisation without substantial cracking of the produced multi-branched hydrocarbons. Multi-branched isomers are in this case defined as compounds containing more than one carbon atom having bond to at least three other neighbouring carbon atoms or containing at least one carbon atom having bond to four neighbouring carbon atoms. Mono-branched isomers are defined as compounds containing just one carbon atom with bonds to three neighbouring carbon atoms. The process can be designed solely for the C_{7+} fraction or cuts containing this fraction (e.g. C_4-C_7, C_5-

C_9, C_7-C_9, C_6-C_7, C_7, C_8 or C_9, C_9-C_{12}) and consisting mainly of paraffins and possibly naphtenes, aromates and olefins.

The main embodiment of the invention is a combination of three oxides and their use in catalytic production of multi-branched C_{7+} isomers. The catalyst comprises zirconia, alumina and tungsten oxide, which are calcined and reacted together at high temperature and impregnated with a Group VIII metal. A catalyst composition comprising a Group VIII metal on mixed oxides behaves differently from noble metal supported on tungstated zirconia or on alumina only. The catalyst composition described by this invention provides a very efficient and mechanically strong catalyst, which reaches high selectivity in C_{7+} isomerisation.

Isomerisation proceeds on Brønsted acid sites and acidity originates from the reaction between tungsten oxide and zirconia. The references (for example E. Iglesia, D.G. Barton, S.L. Soled, S. Miseo, J.E. Baumgartner, W.E. Gates, G.A. Fuentes and G.D. Meitzner, Stud. Surf. Sci. Catal. 101 (1996) 533) disclose that "high isomerisation rates occur on samples with near saturation W surface densities". Such saturation typically occurs at around 15 wt% of tungsten loading. However, as a part of this invention it is shown that excess of tungsten oxide much above formation of tungsten oxide mono-layer on zirconia support has a very positive effect on the selectivity of the catalyst. Unlike claimed in most of the references for C_{5+} isomerisation, the optimum for C_{7+} isomerisation catalyst is in the range of 10% to 50%, most preferentially 20% to 40%. Excess of tungsten oxides might have a positive effect on the concentration of hydrogen on the catalyst surface and therefore

on hydrogen transfer and desorption of isomerisation inter-
mediates before their cracking to gas.

The role of alumina in the catalyst is twofold. Primarily,
addition of alumina significantly increases selectivity to-
wards multi-branched isomers. The most striking effect is
on the rate of formation of isomers with quaternary carbon
atoms like 2,2-dimethylpentane. These isomers posses very
high octane numbers and are difficult to form via classical
carbenium ion mechanism on conventional isomerisation cata-
lysts like sulphated zirconia, chlorinated alumina, hetero-
poly acids, zeolites etc., or on alumina free tungstated
zirconia with low tungsten content. Secondary, alumina im-
proves the mechanical strength of the catalyst. The prepa-
ration of mechanically stable sulphated zirconia catalyst
by addition of alumina is described in several patents for
example in US Patent No. 6,326,328. For the catalyst of
this invention, an alumina content of at least 10 wt% is
required to achieve sufficient strength. The most preferred
catalyst contains between 10% and 50 wt% of alumina.

The quality of the applied zirconia is very important for
the total catalyst performance. Zirconia can be prepared,
for example, by precipitation of zirconyl nitrate or zir-
conyl chloride with ammonia at high pH followed by heating
under reflux, similarly to A. Calafat, Stud. Surf. Sci.
Catal. 118 (1998) 837. The zirconia used for the prepara-
tion of the invented catalyst was dried at 120°C and pos-
sessed a surface area above 300 m^2/g.

The most typical tungsten precursor is ammonium metatung-
state due to its high solubility and low price, while the

most typical aluminium source would be hydrated aluminas, like pseudoboehmite. However, since the origin of these compounds plays a rather inferior role for the catalyst's quality, the list is not limited to the above mentioned ma-
5   terials.

The Group VIII metal may be selected from any of the Group VIII metals and mixtures thereof. The preferred metals are palladium and platinum with a concentration between 0.01
10   wt% to 5 wt%, most preferentially between 0.05 wt% to 1 wt%.

Besides the above mentioned strictly required catalyst components, boron and phosphorous compounds are also known to
15   stabilise zirconia in the tetragonal form, which is the main support for acidic active sites. Therefore, these compounds might also be added with a loading of up to 20 wt% of the dry catalyst.

20   The manufacturing procedure of mechanically strong catalyst extrudates is commonly applied for and known by those skilled in the art. It comprises the following steps:
    (a)   Kneading of the mixture of zirconium and aluminium oxides/hydroxides and tungsten precursor.
25   (b)   Shaping the kneaded mixture.
    (c)   Calcining the mixture at 600-900°C, most preferentially at 650°C-800°C.
    (d)   Impregnation of the catalyst with the Group VIII metal.
30   (e)   Calcination of the resulting material at 300-800°C, most preferentially between 300°C to 500°C.

This standard procedure can as a matter of course be modi-
fied. For example, mixed alumina and zirconia can be pre-
pared by the co-precipitation of both precursors with ammo-
nia, the tungsten precursor can be added after the alumina-
zirconia extrudates have been made and calcined, Group VIII
metal can be added already before the first calcination
step, etc.

The C_{4+} isomerisation reaction on the above mentioned cata-
lyst proceeds in the presence of hydrogen with a hydrogen
to hydrocarbon molar ratio between 0.1 to 5. Typical oper-
ating conditions are temperatures between 150°C to 300°C,
total pressures varying between 1 and 40 bar and liquid
space velocities (LHSV) between 0.1 to 30 h^{-1}. The pre-
ferred conditions are temperatures between 130-250°C,
LHSV=0.5-5 h^{-1}, pressures between 5-15 bar and a hydro-
gen:hydrocarbon ratio between 1 and 3. The feed may option-
ally also include shorter paraffins, aromatics or cyclopar-
affins. When passing such a feed through the reactor bed,
shorter paraffins are also isomerised, while equilibrium is
established between aromatics and corresponding cycloal-
kanes. At typical reaction temperatures, the equilibrium is
shifted towards cycloalkanes. The reaction rate for ring
opening will be very slow.

Specific embodiments of the invention for the production of
a high liquid yield of gasoline with a high research octane
number (RON) are described in more detail below.

Example 1
Zirconium oxide was prepared by adding diluted ammonia wa-
ter to an aqueous solution of zirconyl nitrate and adjust-

ing pH to 9. The mixture was refluxed overnight. The white solid was filtered and washed and dried overnight at 120°C. The dried material had a surface area of 333 m^2/g. 225 g of zirconia, 168 g alumina gel (pseudoboehmite 30 wt%) and 62 g of ammonium metatungstate were mixed for 15 minutes and extruded into 1/16" extrudates. The catalyst was calcined at 700°C for three hours. XRD of the calcined catalyst demonstrate the presence of alumina as shown in Fig. 1. 0.5 wt% Pd was introduced by incipient wetness impregnation. The catalyst was calcined at 350°C before it was placed into the reactor.

Example 2, Comparative Example
Zirconium oxide was prepared by adding diluted ammonia water to an aqueous solution of zirconyl nitrate and adjusting pH to 9. The mixture was refluxed overnight. The white solid was filtered and washed and dried overnight at 120°C. The dried material had a surface area of 333 m^2/g. 225 g of zirconia and 62 g of ammonium metatungstate was mixed with an sufficient amount of water to form an extrudable paste. This paste was mixed for 15 minutes and extruded into 1/16" extrudates. The catalyst was calcined at 700°C for three hours and 0.5 wt% Pd was introduced by incipient wetness impregnation. The catalyst was calcined at 350°C before it was placed into the reactor.

Example 3
Zirconium oxide was prepared by adding diluted ammonia water to an aqueous solution of zirconyl nitrate and adjusting pH to 9. The mixture was refluxed overnight. The white solid was filtered and washed and dried overnight at 120°C. The dried material had a surface area of 333 m^2/g. 225 g of

zirconia, 168 g alumina gel (pseudoboehmite 30 wt%) and 62 g of ammonium metatungstate were mixed for 15 minutes and extruded into 1/16″ extrudates. The catalyst was calcined at 700°C for three hours. 0.5 wt% Pt was introduced by in-
5   cipient wetness impregnation. The catalyst was calcined at 350°C before it was placed into the reactor.

Example 4

Heptane isomerisation with the catalyst prepared according
10 to Example 1 was performed in a fixed bed reactor at 190°C with LHSV=1 h^{-1} at a total pressure of 7 bar and the feed consisting of a hydrogen:hydrocarbon mixture with the ratio of 1:2. A detailed description of the product composition is shown in Table 1.

15

Based on a once-through mode, multi-branched isomers yielded 30% with only 3.1% cracking (liquid yield 91%). Calculated RON of the multi-branched isomer fraction is 88.8.

Table 1

n-Heptane isomerisation at 190°C with LHSV = 1 h^{-1} at
a total pressure of 7 bar and the feed consisting of
a hydrogen:hydrocarbon mixture of a ratio of 1:2.

	Product [wt%]
Propane	1.32
Isobutane	1.70
n-Butane	0.09
Isopentane	0.03
Isohexanes	0.03
2,2-dimethylpentane	9.20
2,4-dimethylpentane	7.68
2,2,3-trimethylbutane	1.07
3,3-dimethylpentane	4.33
2-methylhexane	26.08
2,3-dimethylpentane	7.68
3-methylhexane	24.66
3-ethylpentane	1.69
n-heptane	14.21
Cycloheptanes	0.10

Example 5, Comparative Example

Heptane isomerisation with the catalyst prepared according
to Example 2 was performed in a fixed bed reactor at 190°C
with LHSV=1 h^{-1} at a total pressure of 7 bar and the feed
consisting of a hydrogen : hydrocarbon mixture with the ra-
tio of 1:2. A detailed description of the product composi-
tion is shown in Table 2.

Based on a once-through mode, multi-branched isomers yielded 25.3% with 7.8% cracking (liquid yield 69%). Calculated RON of the multi-branched isomer fraction is 88.9.

Table 2

n-Heptane isomerisation at 190°C with LHSV = 1 h^{-1} at a total pressure of 7 bar and the feed consisting of a hydrogen:hydrocarbon mixture of a ratio of 1:2.

	Product [wt%]
Propane	3.31
Isobutane	4.25
n-Butane	0.12
Isopentane	0.05
Isohexanes	0.07
2,2-dimethylpentane	7.48
2,4-dimethylpentane	6.54
2,2,3-trimethylbutane	0.81
3,3-dimethylpentane	3.08
2-methylhexane	24.21
2,3-dimethylpentane	7.35
3-methylhexane	23.97
3-ethylpentane	1.67
n-heptane	16.85
Cycloheptanes	0.15

The results in Example 4 and Example 5 demonstrate that the catalyst of the invention exhibits higher yield of multi-branched isomers and significantly lower cracking activity.

Example 6

Heptane isomerisation with the catalyst prepared according to Example 1 was performed in a fixed bed reactor at 165°C with LHSV=0.2 h^{-1} at a total pressure of 6 bar and the feed

5 consisting of a hydrogen:hydrocarbon mixture with the ratio of 1:2. A detailed description of the product composition is shown in Table 3.

The catalyst produced on a once-through basis 35.1% of

10 multi-branched isomers with only 3.2% cracking (liquid yield 92%). Calculated RON of the multi-branched isomer fraction is 89.2.

Table 3

n-Heptane isomerisation at 165°C with LHSV = 0.2 h^{-1}
at a total pressure of 7 bar and the feed consisting
of a hydrogen:hydrocarbon mixture of a ratio of 1:2.

	Product [wt%]
Propane	1.34
Isobutane	1.74
n-Butane	0.07
Isopentane	0.03
Isohexanes	0.03
2,2-dimethylpentane	11.66
2,4-dimethylpentane	9.02
2,2,3-trimethylbutane	1.22
3,3-dimethylpentane	4.84
2-methylhexane	25.52
2,3-dimethylpentane	8.32
3-methylhexane	23.2
3-ethylpentane	1.49
n-heptane	11.30
Cycloheptanes	0.10

Example 7

A sample of a catalyst according to Example 1 was analysed
by x-ray diffraction.

The result was printed out as a spectrogram shown on Fig.
1.

The x-axis is the 2 θ range at which the analysis was per-
formed. At 32°, 37.5°, 39.5°, 46°, 61° and 67° peaks occur
proving the presence of eta-alumina.

5   This clearly indicates that aluminium is present as alumina
in the structure of the active part of the catalyst.